## NOTES:

- 1. SUBSTRATE: UV FUSED SILICA
- 2. SURFACE S2 TO BE PARALLEL WITH SURFACE S1 TO WITHIN 5 arcsec


3. COATING (APPLY ACROSS COATING APERTURE)
S1: HARD DIELECTRIC SPUTTERED
T(avg): ≥91% FROM 1020 - 1650nm @ 0° AOI
T(avg):≤0.01% FROM 200 - 980nm @ 0° AOI
T(abs):=50% FOR 1000±10nm @ 0° AOI


S2:SINGLE LAYER MgF2


## 4. FINE GRIND SURFACE


- 5. POWER, IRREGULARITY, AND SURFACE QUALITY SPECIFICATIONS APPLY ACROSS CLEAR APERTURE
- 6. TRANSMITTED WAVEFRONT DISTORTION, RMS: ≤λ/4 @ 633nm (prior to coating)
- 7. ROHS COMPLIANT











LONGPASS FILTER

|                 | \$1                  | \$2                  |
|-----------------|----------------------|----------------------|
| SHAPE           | PLANO                | PLANO                |
| SURFACE QUALITY | 60-40                | 60-40                |
| CLEAR APERTURE  | >80%                 | >80%                 |
| BEVEL           | PROTECTIVE AS NEEDED | PROTECTIVE AS NEEDED |

SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

## Edmund Optics®

|                        |    |        | •  |  |
|------------------------|----|--------|--|--|
| THIRD ANGLE PROJECTION |    | TITLE  | Ø50mm, 1000nm, HIGH PERFORMANCE<br>LONGPASS FILTER |  |
| ALL DIMS IN            | mm | DWG NO | 84766 SHEET 1.0F.1                                 |  |